

Amendments to the Specification

Please amend Table 3 on page 27 as follows:

Binder	typical low frequency permittivity (ϵ)
Poly(ethylene/tetrafluoroethylene)	2.6
poly(ethylene/chlorotrifluoroethylene)	2.3
fluorinated ethylene/propylene copolymer	2-2.5
polystyrene-co- α -methylstyrene	2.5-2.6
ethylene/ethyl acrylate copolymer	2.8
poly(styrene/10%butadiene)	2.6
poly(styrene/15%butadiene)	2.6
poly(styrene/2,4 dimethylstyrene)	2.5
Topas TM (all grades), cyclic olefin copolymer	2.2-2.3